Hydrogel FL- 3: Specifications	
Appearance	Cream Coloured Homogeneous Powder
Moisture	11.0 % Maximum
Protein	15.00 % Maximum
Acid Ins. Residue	15.00 % Maximum
Gum Content	59.00 % Minimum by difference
Mesh Thru 200 Mesh	80.00 % Min
Screen	
Viscosity 1 % Solution	300 cps Min after 02 hours, Using Brookfield
	Viscometer Model,
	RVT spindle No. 2 with temperature exactly at 25oC
	and at 20 rmp.
Ph	5.5 – 7.5
Packing	Multiple Kraft paper bags with poly liner inside. Net
	weight 25 kgs
Storage	Store in cool, dry place